



■ 建 材

製品名 Articles	白色度 Whiteness (%)	水分 Moisture (%)	見掛け密度 Apparent Density (g/ml)	メタン径 D50 Average Particle Size (μm)
FS404	89	0.4	0.15	5
MS412	87	0.3	0.30	12
RL119	95	0.1	0.40	17
RL217	93	0.2	0.50	20
RG319	90	0.2	0.51	19
RH415	87	0.3	0.42	14
RS415	87	0.3	0.45	15
RS515	83	0.3	0.47	15
RS613	78	0.4	0.42	13

■ 接着剤

製品名 Articles	白色度 Whiteness (%)	水分 Moisture (%)	見掛け密度 Apparent Density (g/ml)	メタン径 D50 Average Particle Size (μm)
FH104	96	0.3	0.13	4
FH105	96	0.2	0.15	5
FH106	95	0.3	0.16	6
FH108	95	0.3	0.17	8
FS404	89	0.4	0.15	5
MG115	94	0.2	0.33	14
MS410	87	0.3	0.24	10
MS412	87	0.3	0.30	12